

Tarmac provides a comprehensive sales and technical advisory service to specifiers and customers.

PRICES AND CONDITIONS OF SALE

All quotations given, orders placed and materials supplied are subject to the Conditions of Sale available via download from the Tarmac website www.tarmac.co.uk or upon request from your nearest Tarmac Sales Office.

Tarmac Truscreed and Truscreed **[HD]** is available direct from Tarmac: factories located strategically throughout the United Kingdom: contact your nearest Local Sales Office for further details - see heading Further Information.

When ordering, state the product designation, quantity, date and time of delivery. 24 hours should normally be allowed for delivery.

Bulk loads in tipper road trucks generally up to 10/20 tonnes or 7-8 tonne steel skips (where available). The skips reduce wastage, and prevent contamination.

Product Data Sheet No. 12

SCREEN

Revised October 2005

INTRODUCTION

ADVANTAGES

- Significantly reduced drying times (to accept final flooring)
- Better working properties providing easier and more reliable compaction
- Quicker early strength development
- Reduced drying shrinkage resulting from low water/cement ratio
- Good resistance to construction traffic and dusting
- Greater final strength

Tarmac Truscreed and Truscreed **[HD]** have the following additional advantages over other specialist screed materials which are generally site mixed

Better cement dispersion gives greater and more uniform compressive strength throughout the floor area

Factory mixing takes quality control away from the site and into the factory, providing consistent quality materials and accurate proportioning.

Use in accordance with recommendations in code of practice BS 8204-1. The British standard listing traditional proportions for ready-to-use cement sand screeds was BS 4721 which was withdrawn in February 2005. Tarmac factory produced screed materials conform to the requirements of BS EN 13183.

Truscreed and Truscreed[HD] should be used in accordance with the recommendations of Codes of practice BS 8000:Part 9 and BS 8204:Part 1.

Tarmac Truscreed and Truscreed **HD** are thoroughly mixed accurately controlled blends of the following materials:

- Well-graded washed fine aggregate (sand) to BS EN 12620 / BS EN 13139
- Portland Cement to BS EN 197-1
- Retarding /water reducing admixture conforming to BS EN 934-2/3 giving the optimum working time, normally usable for 8 - 12 hours from the time of mixing

- Where it is intended to pump the material, notify your local sales office allowing reasonable time before work is due to commence

Typical test results

Fresh wet uncompacted	1,850 - 2,000 kg/m ³
Compacted set and air dried	2,000 - 2,200 kg/m ³

STRENGTH

Results based on prisms made, cured and tested in accordance with the requirements of BS EN 13892-2.

SCREED DESIGNATION	BS EN 13813 COMPRESSIVE STRENGTH CLASS	BS EN 13813 FLEXURAL STRENGTH CLASS
Truscreed	C25	F3.0
Truscreed H.D.	C30	F4.0

Table 1 : Truscreed and Truscreed HD strength classes and minimum strength

These results are indicative and may be subject to change as further test results become available.

Tarmac Truscreed **[HD]** is designed for use where high point loading or heavy trafficking is expected.

Light foot traffic	2 days
Site traffic	5 days

Allow approximately 5-7 days per 25 mm of thickness. If the screed is very thick, or the concrete base has an excessive moisture content, this time may be increased. High humidity or low temperatures will also delay the drying out process. As the drying time indicated applies from completion of any curing operation, the flooring contractor must check the moisture content of the screed before laying the floor finish.

Tarmac Truscreed and Truscreed **[HD]** contain less than 1.0% organic material and are classified in accordance with BS EN 13501-1 as Class A1 without testing (Commission Directive 96/603/EC).

Further Information:

For further technical information please call: **08701 116 116.**

EFFECT OF FROST

In cold conditions adequate precautions must be taken to protect from frost attack. No antifreeze chemicals or accelerating admixtures should be added to the screed material.

COMPATIBILITY

Tarmac Truscreed and Truscreed [HD] are compatible with all normal building materials, but wet cementitious materials may attack certain metals eg Aluminium.

DURABILITY

No problems should occur if the correct screed material has been specified, but neither Tarmac Truscreed nor Truscreed [HD] are designed as a wearing surface and should be covered with a flooring material.

Health & Safety

There is a real danger of Contact Dermatitis or serious burns if skin comes into contact with wet cement mixes such as fresh concrete, mortar or screed. Wear suitable protective clothing and eye protection. Where skin contact occurs, either directly or through saturated clothing, wash immediately with soap and water. For eye contact, immediately wash out eye thoroughly with clean water. If swallowed wash out mouth and drink plenty of water.

For further information refer to Tarmac Safety Data Sheet No. 17.

Applications

USES

Suitable for use on the following bases:

1. Solid concrete ground floor slabs:
 - a) directly in contact with the slab (bonded)
 - b) with suitable damp proof membrane between slab and screed (unbonded)
 - c) over an insulating layer to isolate the screed from the base (floating).
2. Precast concrete units or beams with reinforcement.
3. In situ suspended floors.
4. As a topping to lightweight screeds based on perlite or other lightweight aggregates.
5. Certain other situations - refer to your nearest Local Sales Office.

The above applications are subject to the minimum thicknesses given in the section on Construction/Sitework.

Table 2 - Tarmac Truscreed/Truscreed [HD]

TYPE OF SPECIFICATION	RECOMMENDED MINIMUM AVERAGE THICKNESS (mm)	MINIMUM THICKNESS AT ANY POINT (mm)	COMMENTS
Monolithic (i.e. applied within 3 hours of placing concrete)		Ideally 12 - 15 Not greater than 25	Thicknesses greater than 25 mm should be avoided to minimise shrinkage stresses
Grouted to precast concrete slab cement: water slurry	45	30	Brushing of green concrete or mechanical treatment to expose aggregate recommended
Grouted to concrete planks with cement: water slurry	60	40	Screed should be reinforced if structural movement is expected. Cement: Tarmac SB Admixture slurry* may be used to ensure a better bond. Surface of units must be roughened to form a key
Grouted to sound, rough concrete slab with cement: Tarmac SB Admixture slurry*	40	15	Brushing of green concrete or mechanical treatment to expose aggregate below 40mm
Grouted to waterproof concrete slab with cement SB admixture slurry	50	45	Aggregate must be exposed
Grouted on bitumen dpm using cement: Tarmac SB Admixture slurry*	50	45	
Unbonded	55	50	
Applied to concrete stairs Treads Risers		20 12 (15 max)	Aggregate must be exposed by mechanical treatment and cement: Tarmac SB Admixture slurry* applied
Toppings to lightweight screeds †	13	10	Applied to lightweight aggregate screeds, eg Limelite Lightweight Screed. Pre-wetting of lightweight screeds may be necessary
Pipes and conduits		25 cover	Reinforced with wire mesh over
Trunkings		25 cover	Reinforced with wire mesh over and bonded to trunking with cement: Tarmac SB Admixture slurry*. Trunkings must be securely bedded and fixed
Floating screed for sound insulation on 5mm polyethylene foam	50	40	Reinforced with D49 or similar unless over 55 mm, slurry grout to foam insulation
Floating screed for thermal insulation on fibre quilt	70	65	Screed reinforced with D49 or similar below 75 mm
Floating screed for thermal/sound insulation on rigid board	55	50	Reinforced with D49 or similar below 60 mm

* Used according to Tarmac Product Data Sheet No.22
† Where used in conjunction with Limelite Lightweight Screed apply monolithically if possible.
** Fibres may be used to replace crack control reinforcement (D49)

One tonne of screed material will have an approximate volume of 0.43 - 0.48 m³. Table 3 shows the coverage area per tonne for a range of thicknesses.

THICKNESS mm	COVERAGE AREA m²/tonne (approx)	THICKNESS mm	COVERAGE AREA m²/tonne (approx)
10	45.0	45	10.0
15	30.0	50	9.0
20	22.5	55	8.2
25	18.0	60	7.5
30	15.0	65	7.0
35	13.0	70	6.5
40	11.0	75	6.0

Table 3: Approximate coverage area of screed material

NOTE: Slight variations in sub-base levels will affect the coverage

Construction/Sitework

SITE STORAGE

Tarmac Truscreed and Truscreed [HD] should be tipped on to a clean banker board with a sealed base and sheeted to protect it from the elements. Do not tip new deliveries onto the remains of the previous load.

PREPARATION

The base concrete must be clean and in particular free from lime, gypsum, plaster, dust, dirt, oil or grease. The base concrete should be swept to remove all loose material and wetted with clean water, where the levelling screed is to be placed in direct contact with the base. Just before laying the screed an appropriate bonding material should be brushed into the surface, care being taken that this neither forms deep pools nor dries before the screed is placed.

APPLICATION

BONDED CONSTRUCTION

(Minimum thickness 40 mm)

The bond between the base and levelling screed will depend on the thoroughness with which the base has been prepared. A bonding agent such as Tarmac SB Admixture can be used to obtain a good bond. The bonding agent should be used in a slurry with cement in place of the normal cement + water slurry (3 volumes cement :2 volumes Tarmac SB Admixture) and the screed laid before the slurry dries or sets.

UNBONDED CONSTRUCTION

(Minimum thickness 50 mm)

When no bond is possible between levelling screed and base, the screed should be at least 50 mm thick, or, if containing heating pipes a minimum of 65 mm thick.

FLOATING SCREED

(Minimum thickness 75 mm / 65 mm for light loading)

A levelling screed laid on a compressible layer such as thermal or sound insulating material, should be at least 65 mm thick, or, if containing heating pipes, a minimum

of 75 mm thick. All conduits should be firmly fixed covered with suitable crack control mesh and given a minimum cover of 25 mm.

Where Tarmac Truscreed or Truscreed [HD] are laid on thermal or sound insulation boards, which are sufficiently rigid to enable the screed to be properly compacted, the minimum thickness of the Tarmac Truscreed or Truscreed [HD] may be reduced to 55 mm.

TOPPING TO LIGHTWEIGHT SCREEDS

A smooth surface can be given to lightweight screeds, which, will enable point loadings to be carried.

The normal thickness will be of the order of 10 - 15 mm and, if necessary, the suction of the lightweight screed should be controlled by wetting with clean water.

LAYING

Reference should be made to Code of practice BS 8204-1

The material should be spread on the prepared base with adequate surcharge. It is important to compact the screed material thoroughly and evenly over the whole area, either by tamping or by mechanical means and then level with a screed board. For many floor finishes, the screed must be finished with a steel trowel to give it a smooth dense surface. For such a finish, the screed should be allowed to stiffen slightly and then worked with the trowel, which will make a ringing sound when the correct action is being used excessive trowelling should be avoided as this brings a layer of cement laitance to the surface where it may craze and dust.

To aid compaction of thicker cement sand levelling screeds, i.e. over 50 mm thickness, the screed may be laid in two layers. Both layers should be of approximately equal thickness and the same mix and water content.

The first layer should be thoroughly compacted using heavy tamping or a weighted roller the second layer should be laid as soon as possible, i.e. within 2 hours, after compaction of the lower layer (monolithically)

The most common cause of screed failure is poor compaction.

CURING

Screeds should be protected from damage after laying. To achieve the full performance of Tarmac Truscreed and Truscreed [HD] adequate curing is essential and the screed should be covered with plastic sheeting or other suitable material to retain moisture for at least seven days. Whilst damping down of the surface before covering is acceptable, saturation of the screed, e.g. by prolonged hosing is not recommended

NOTE: Do not use hot air blowers, underfloor heating, or other means of accelerating drying in the early life of the screed